

Lindau

7028.01 - 7028.33



Product

Upholstery

Description

2-colour woollen upholstery fabric that can be used on both sides

Composition

80% wool / 20% polyamide

Width

± 140 cm, ± 55 inches

Weight

± 536 gr/m², ± 17 oz/yd²

Flame retardancy

EN 1021/1-2 , Pass

BS 5852 , Crib 5

Cal TB 117-2013, section 1 , Pass

IMO 2010 FTP part 8 , Pass

NFPA 260 , Class 1

Abrasion

ISO 12947-2 , 100.000 rubs Martindale

ASTM D3597/D4157 (#10 cotton duck) , 45.000 double rubs Wyzenbeek

Pilling

ISO 12945-2

3 (scale 1-5)

ASTM D3511

2,5 (scale 1-5)

Colorfastness to crocking

ISO 105 X12

wet 4 (scale 1-5) / dry 4-5 (scale 1-5)

AATCC 8

wet 5 (scale 1-5) / dry 4.5 (scale 1-5)

Colorfastness to light

ISO 105 B02

Light 4-5 / dark 4-5 (scale 1-8)

AATCC 16.2 opt.1 or 16.3 opt. 3

5 (scale 1-5)

Seam slippage

ISO 13936-2 - warp

4 mm

ISO 13936-2 - weft

3.5 mm

ASTM D4034 - warp

39 lbs

ASTM D4034 - weft

89 lbs

Breaking strength

ASTM D5034 - warp

186 lbs

ASTM D5034 - weft

224 lbs

Labels



USCG -
EU MRA
0038



STANDARD
100
S10-0100
Hohenstein HTTI

Care & Maintenance



Shrinkage

Lindau

7028.01 - 7028.33

7028.01	7028.15	7028.13	7028.04	7028.09	7028.22	7028.19	7028.20	7028.26
7028.02	7028.14	7028.10	7028.08	7028.18	7028.21	7028.23	7028.32	7028.30
7028.03	7028.12	7028.07	7028.11	7028.31	7028.28	7028.24	7028.29	7028.33
7028.06	7028.05	7028.16	7028.17	7028.27	7028.25			